

ICLAM General Specifications sheet of PVC Belting

New Code	Ply	Total thick mm	Mtrl	Top cover (mm)				Top cover (mm)				As	Other Character	Temp. °C		Weft	Load N/mm		Max n l. 14			
				Colour	Thick	Surface	Shore A	Thick	Surface	Shore A	Min			Max	Load		1% N					
1/10 S/B AG	1	1.0	V	Apple Green	0.5	Glossy	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	20	30	60	4	3000
2/20 S/B AG	2	2.0	V	Apple Green	0.5	Glossy	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	40	60	120	8	3000
2/30 S/B AG	2	3.0	V	Apple Green	1.1	Glossy	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	60	80	120	8	3000
3/40 SB AG	3	4.0	V	Apple Green	1.1	Glossy	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	80	100	170	13	3000
3/50 S/B AG	3	5.0	V	Apple Green	1.5	Glossy	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	90	110	170	13	3000
4/60 S/B AG	4	6.0	V	Apple Green	1.5	Glossy	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	100	120	200	20	3000
5/80 S/B AG	5	8.0	V	Apple Green	2.4	Glossy	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	120	140	250	25	3000
3/70 S/B PG H	3	7.0	V	Petrol Green	3.8	Glossy	55	~	~	~	Fabric	~	Y	LN	-10	80	Rigid	80	150	170	15	3000
2/20 S/B PG	2	2.0	V	Petrol Green	0.5	Glossy	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	40	60	120	8	3000
3/40 S/B PG	3	4.0	V	Petrol Green	1.1	Glossy	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	80	100	170	13	3000
1/10 M/B W FDA	1	1.0	V	White	0.5	Matt	80	~	~	~	Fabric	~	N	FDA	-10	80	Rigid	20	30	60	4	3000
2/20 S/B W FDA	2	2.0	V	White	0.5	Glossy	75	~	~	~	Fabric	~	N	FDA	-10	80	Rigid	40	60	120	8	3000
2/30 S/B W FDA	2	3.0	V	White	1.1	Glossy	75	~	~	~	Fabric	~	N	FDA	-10	80	Rigid	60	80	120	8	3000
3/40 S/B W FDA	2	4.0	V	White	1.1	Glossy	75	~	~	~	Fabric	~	N	FDA	-10	80	Rigid	80	100	120	13	3000
3/50 S/B W FDA	3	5.0	V	White	1.5	Glossy	75	~	~	~	Fabric	~	N	FDA	-10	80	Rigid	90	110	170	13	3000
4/60 S/B W FDA	4	6.0	V	White	1.5	Glossy	75	~	~	~	Fabric	~	N	FDA	-10	80	Rigid	100	120	200	13	3000
2/20 S/B BL	2	2.0	V	Blue	0.5	Glossy	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	40	60	120	8	3000
2/20 M/B BK	2	2.0	V	Black	0.5	Matt	80	~	~	~	Fabric	~	Y	~	-10	80	Rigid	40	60	120	8	3000
3/40 M/B BK	3	4.0	V	Black	1.1	Matt	80	~	~	~	Fabric	~	Y	~	-10	80	Rigid	80	100	170	13	3000
2/26 M/B PG	2	2.6	V	Petrol Green	1.0	Matt	80	~	~	~	Fabric	~	Y	LN	-10	80	Rigid	60	80	140	10	3000
2/22 D/B AG	2	2.2	V	Apple Green	0.8	Diamond	75	~	~	~	Fabric	~	Y	~	-10	80	Rigid	40	60	120	8	3000
2/30 S/D AG	2	3.0	V	Apple Green	0.7	Glossy	75	V	AG	0.6	Diamond	75	N	~	-10	80	Rigid	60	80	120	8	3000
3/50 S/D AG	3	5.0	V	Apple Green	0.6	Glossy	75	V	AG	0.8	Diamond	75	N	~	-10	80	Rigid	80	100	170	18	3000
3/50 S/D AG FLEX	3	5.0	V	Apple Green	0.6	Glossy	75	V	AG	0.8	Diamond	75	N	Flex	-10	80	Flexible	70	90	170	18	3000
2/23 D/B W FDA	2	2.3	V	White	0.8	Diamond	75	V	~	~	Fabric	~	N	FDA	-10	80	Rigid	40	60	120	8	3000
2/30 S/D W FDA	2	3.0	V	White	0.7	Glossy	75	V	AG	0.6	Diamond	75	N	FDA	-10	80	Rigid	60	80	120	8	3000
2/30 M/D W FDA	2	3.0	V	White	0.7	Matt	75	V	AG	0.6	Diamond	75	N	FDA	-10	80	Rigid	60	80	120	8	3000
3/50 S/D W FDA	3	5	V	White	0.8	Glossy	75	V	White	0.8	Diamond	75	N	FDA	-10	80	Rigid	90	110	170	13	3000
2/30 S/D W FDA FLEX	2	3.0	V	White	0.7	Glossy	75	V	AG	0.6	Diamond	75	N	FDA, Flex	-10	80	Flexible	60	80	120	12	3000
2/30 S/D BL	2	3.0	V	Blue	0.7	Glossy	75	V	BL	0.6	Diamond	75	N	~	-10	80	Rigid	60	80	120	8	3000
4/40 S/S PG	4	4.0	V	Petrol Green	0.2	Glossy	75	V	PG	0.2	Glossy	75	N	HR	-10	80	HRigid	70	90	200	20	3000
2/41 S/S W FDA FLEX	2	4.1	V	White	1.0	Glossy	75	V	White	1.0	Glossy	75	N	FDA, Flex	-10	80	Flexible	60	80	120	12	3000
3/62 S/S W FDA FLEX	3	6.2	V	White	2.0	Glossy	75	V	White	1.0	Glossy	75	N	FDA, Flex	-10	80	Flexible	90	110	170	18	3000
1/30 S/S W	1	3.0	V	White	1.5	Glossy	75	V	White	1.0	Glossy	75	N	~	-10	80	Rigid	20	30	60	4	3000
1/30 S/S AG	1	3.0	V	Apple Green	1.5	Glossy	75	V	AG	1.0	Glossy	75	N	~	-10	80	Rigid	20	30	60	4	3000
2/30 M/M BK	2	3.0	V	Black	0.7	Matt	75	V	Black	0.7	Matt	75	N	~	-10	80	Rigid	60	80	120	8	3000
2/18 B/B W	2	1.8	~	~	~	Fabric	~	~	~	~	Fabric	~	Y	FDA	-10	80	Rigid	40	60	120	8	3000
3/30 B/B W	3	3	~	~	~	Fabric	~	~	~	~	Fabric	~	Y	FDA	-10	80	Rigid	80	100	170	12	3000
2/20 F/F YL FLEX	2	2.0	V	Yellow	~	Fabric	~	V	Yellow	~	Fabric	~	N	Flex	-10	80	Flexible	60	80	120	12	3000
2/20 C/C W	2	2.0	V	~	~	Cotton	~	~	~	~	Cotton	~	N	FDA	-10	80	Rigid	50	70	110	7	3000
3/30 C/B W	3	3.0	V	~	~	Cotton	~	~	~	~	Fabric	~	Y	FDA	-10	80	Rigid	80	100	150	11	3000
2/27 HC/HC W	2	2.7	V	~	~	HC	~	~	~	~	HC	~	N	FDA	-10	80	Rigid	60	80	140	12	3000
1/13 D/B BK	1	1.3	V	Black	0.8	Diamond	75	~	~	~	Fabric	~	Y	LN	-10	80	Rigid	20	30	70	5	3000
2/22 D/B BK	2	2.2	V	Black	0.7	Diamond	75	~	~	~	Fabric	~	Y	LN	-10	80	Rigid	40	60	140	10	3000
1/18 GF/B BK	1	1.8	V	Black	1.0	Golf	75	~	~	~	Fabric	~	Y	LN	-10	80	Rigid	20	30	70	5	3000
2/22 GF/B BK	2	2.2	V	Black	0.7	Golf	75	~	~	~	Fabric	~	Y	LN	-10	80	Rigid	40	60	140	10	2000
2/50 RT1/B AG	2	5.0	V	Apple Green	3.0	RT1	60	~	~	~	Fabric	~	N	LN	-10	80	Rigid	60	80	140	10	3000
2/50 RT1/B PG	2	5.0	V	Petrol Green	3.0	RT1	45	~	~	~	Fabric	~	N	LN	-10	80	Rigid	60	80	140	10	3000
2/50 RT2/B AG	2	5.0	V	Apple Green	3.1	RT2	45	~	~	~	Fabric	~	N	LN	-10	80	Rigid	60	80	140	10	2000
2/28 LR1/B BK FR	2	2.8	V	Black	1.3	LR1	35	~	~	~	Fabric	~	Y	LN, FR	-10	80	Rigid	60	80	140	10	3000
2/30 LR2/B PG	2	3.0	V	Petrol Green	1.3	LR2	45	~	~	~	Fabric	~	Y	~	-10	80	Rigid	60	80	140	10	3000
2/27 BW/B PG	2	2.7	V	Petrol Green	1.2	BW	60	~	~	~	Fabric	~	Y	~	-10	80	Rigid	60	80	140	10	3000
2/50 BN/B PG	2	5.0	V	Petrol Green	3.2	BN	60	~	~	~	Fabric	~	Y	~	-10	80	Rigid	60	80	120	8	2000
3/85 BS/B PG	3	8.5	V	Black	5.5	BS	60	~	~	~	Fabric	~	N	~	-10	80	Rigid	80	100	170	13	2000
2/46 ST/B W	2	4.6	V	White	3.0	ST	55	~	~	~	Fabric	~	N	~	-10	80	Rigid	60	80	120	8	3000
3/60 S/ST AG	3	6.0	V	Apple Green	0.5	Glossy	75	V	AG	3.0	ST	55	N	~	-10	80	Rigid	90	110	170	13	3000
3/70 SN/F PG	3	7.0	V	Petrol Green	2.0	SN	75	~	AG	~	Fabric	~	N	~	-10	80	Rigid	100	120	180	30	2000
4/90 SN/F PG	4	9.0	V	Petrol Green	2.0	SN	75	~	AG	~	Fabric	~	N	~	-10	80	Rigid	100	120	220	40	2000
2/50 FB/B W FDA	2	5.0	V	White	3.0	FB	60	~	~	~	Fabric	~	N	FDA	-10	80	Rigid	60	80	120	8	2000
1/35 S/SW120 BK	1	3.5	V	Black	1.8	Glossy	75	V	Black	0.1	Friction	~	N	~	-10	80	Rigid	80	100	200	13	2000
1/45 S/SW150 BK	1	4.5	V	Black	1.8	Glossy	75	V	Black	0.1	Friction	~	N	~	-10	80	Rigid	100	120	250	17	2000
1/60 CR/SW120 BK	1	6.0	V	Black	4.2	CR	60	V	Black	0.1	Friction	~	N	~	-10	80	Rigid	80	100	200	13	2000
1/40 F/F SW125 BK	1	4.0	V	Black	0.1	Friction	~	V	Black	0.1	Friction	~	N	FR	-10	80	Rigid	80	100	200	13	2000
1/40 F/B SW125 BK	1	4.0	V	Black	~	Friction	~	V	Black	~	Brushed	~	N	FR	-10	80	Rigid	80	100	200	13	2000
2/40 S/B RED RV	2	4.0	V+Nrb	Red	2.5	Glossy	32	~	~	~	Fabric	~	N	~	-10	80	Rigid	40	60	120	10	3000
2/50 LR2/B RED RV	2	5.0	V+Nrb	Red	3.5	LR2	32	~	~	~	Fabric	~	N	~	-10	80	Rigid	40	60	120	10	3000
1/33 FELT/B W	1	3.3	FELT	White	~	Felt	~	~	~	~	Fabric	~	N	~	-10	80	Rigid	30	40	70	6	2000